

TECHNICAL DATA SHEET


KAYAPP

Product Name: **bidim**

Reference No: DS GNRL A12 0845-02/2019 Rev2

Date of Issue: 21 May 2019

Description: Nonwoven, Needle punched, Continuous Filament, Polyester Geotextile
 Manufactured in RSA by Kaytech Atlantis, an ISO 9001:2008 accredited facility
 (Registration No: LS 1176)

A12

Mechanical Properties				
Mass		gsm	1200	SANS 9864 / ISO 9864
Thickness	Under 2 kPa	mm	7.4	SANS 9863-1 / ISO 9863-1
Tensile Strength (200mm wide strip)	Weaker Direction	Typical kN/m	80	SANS 1525 / ISO 10319
	Elongation	%	50-70	
Static Puncture Strength	CBR	Typical kN	14.1	SANS 12236 / ISO 12236
Puncture Resistance	Diameter of hole (max)	mm	0	SANS 13433 / ISO 13433
Trapezoidal Tear Strength	Weaker Direction	Typical N	2200	ASTM D4533
Grab Strength	Weaker Direction	Typical N	6000	ASTM D4632
	Elongation	%	50-80	
UV Stability	80 % Strength retained after 500 hours			ASTM D4355
Hydraulic Properties				
Normal Throughflow	@ 50mm head	ℓ/s/m ²	20	SANS 11058 / ISO 11058
Flow Velocity	Calculation based on Throughflow & thickness	m/s	0.020	
Permeability		x10 ⁻³ m/s	2.96	
In-plane Throughflow	20 kPa load l = 1.0	ℓ/hr (per m width)	216	ISO 12958
Pore Size	O _{95W}	µm	< 75	SANS 12956 / ISO 12956
Roll Dimensions				
Width	Standard	m	3 & 6	
Length	Standard	m	50	

The above values are Typical values and are determined from the specified tests carried out by an accredited laboratory. To ensure this information is current please contact your local Kaytech sales office.

Kaytech reserves the right to make technical modifications to its products.

The information given in Kaytech's documentation is to the best of our knowledge true and correct. However, new research results and practical experience can make revisions necessary. No guarantee or liability can be drawn from the information mentioned herein. Furthermore, it is not Kaytech's intention to violate patents or licenses.