

TECHNICAL DATA SHEET

Product Name: **bidim®**
Reference No: DS FLTR 0587-02/2015 Rev 3
Description: "A" Range Nonwoven, Needle punched, Continuous Filament, Polyester Geotextile
Manufactured in RSA by Kaytech Atlantis, an ISO 9001:2008 accredited facility (Registration No: LS1176)

			A1	A2	A3	A4	A5	A6	A7	A8	A10		
Mechanical Properties													
Thickness	Under 2 kPa	mm	1.2	1.4	1.6	1.8	2.6	3.1	4.4	5.2	6.4	SANS 9863-1:13 / ISO 9863-1:05	
Tensile Strength (200mm wide strip)	Weaker Direction	Typical kN/m	7.8	9.0	11.5	14.0	19.5	26.0	40.0	50.0	56.0	*SANS 1525:13 / ISO 10319:08	
		MARV kN/m	7.0	8.1	10.3	12.6	17.2	22.2	35.0	46.0	50.0		
	Elongation	%	50 – 70										
Static Puncture Strength	CBR	Typical kN	1.5	1.9	2.2	2.7	3.6	4.8	7.1	9.5	11.7	*SANS 12236:13 / ISO 12236:06	
		MARV kN	1.3	1.7	2.0	2.5	3.4	4.3	6.5	9.0	11.0		
Puncture Resistance	Diameter of hole (max)	mm	30	27	25	19	16	13	8	6	3	SANS 13433:13 / ISO 13433:06	
Trapezoidal Tear Strength	Weaker Direction	Typical N	240	320	375	440	600	800	1200	1600	2100	ASTM D4533	
		MARV N	205	245	330	375	500	650	1050	1330	1950		
Grab Strength	Weaker Direction	Typical N	500	600	730	900	1250	1550	2500	3260	4700	ASTM D4632	
		MARV N	450	525	700	850	1100	1410	2100	2815	3700		
	Elongation	%	50 - 80										
UV Stability	70% strength retained after 1000 hours										ASTM D4355		
Hydraulic Properties													
Normal Throughflow	@ 50mm head	l/s/m ²	200	150	125	100	80	70	45	30	20	SANS 11058:13 / ISO 11058:10	
In-plane Throughflow	Flow Rate (per m width)	l/hr	20	30	35	40	50	55	75	120	130	ISO 12958:10	
Permeability	@ 50mm head	m/s x10 ⁻³	4.8	4.2	4.0	3.6	4.2	4.3	4.0	3.1	2.6	SANS 11058:13 / ISO 11058:10	
Pore Size	O ₉₅ W	µm	200	170	155	138	132	130	114	< 75	< 75	SANS 12956:13 / ISO 12956:10	
Roll Dimensions													
Width	Standard	m	1.32, 1.76, 2.65, 3.53 & 5.3					2.65 & 5.3					
Length	Standard	m	150	150	150	150	150	75	75	50	50		

The above values include both Typical and Minimum Average Roll Values (MARV) and are determined from the specified tests carried out by an accredited laboratory. To ensure this information is current please contact your local Kaytech sales office.

* Ten specimens per test according to SANS 9862:13 / ISO 9862:05 "Sampling and Preparation of Specimens"

Kaytech reserves the right to make technical modifications to its products.

The information given in Kaytech's documentation is to the best of our knowledge true and correct. However, new research results and practical experience can make revisions necessary. No guarantee or liability can be drawn from the information mentioned herein. Furthermore, it is not Kaytech's intention to violate patents or licenses.